

# TECHNICAL DATA

## KÄHR'S LUXURY TILES

### CLICK 5 mm WOOD AND STONE



**Click Stone** 300 x 600 x 5 x 0.30 mm  
2.16 m<sup>2</sup>/box, 48 box/pallet






**Click Wood** 172 x 1210 x 5 x 0.30 mm  
2.08 m<sup>2</sup>/box, 50 box/pallet

#### PRODUCT













Click LVT Rigid Core SPC+ IXPE	EN ISO 10582	Luxury Vinyl Tile
Joint		Click 5G
Application	EN ISO 10874	23/31



#### SPECIFICATION

Thickness		EN ISO 24337	5.0 mm (integrated IXPE damping)
Weight		EN ISO 24342	7.87 kg/m <sup>2</sup>
Wear layer		EN ISO 24346	0.30 mm

#### PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, FloorScore, A+
Fire resistance	 EN 13501-1	B <sub>f</sub> -s1
Residual indentation	 EN ISO 24343-1	< 0.2 mm (integrated IXPE damping)
Dimensional stability	 EN ISO 23999 (80 °C/6 h)	< 0.1%
Colour fastness	 EN ISO 105-B02	≥ 6
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R10
Electrical propensity	 EN 1815	< 2 kV (antistatic)
Wear and scratch resistance	 EN 16094	Pass with good results
Chemical resistance	 EN ISO 26987	Pass with good results
Thermal resistance	 EN 12664:2001	0.032 m <sup>2</sup> K/W
Effect of castor chair	 EN 425	Suitable
Underfloor heating		Ok (max +27 °C)
Impact sound reduction	 EN ISO 10140	ΔL <sub>w</sub> = 20 dB (integrated IXPE damping)
Resistance to bacteria and fungi		Good