

Test No: 144713

Independent Textile
Testing
Service, Inc.

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: UPOFLOOR

May 27, 2014

Subject: One sample of vinyl floor covering submitted by the customer and identified as below.

Sample Identification: Xpression 1171
Batch 4010
Date of Manufacturing: 14th Feb. 2014
Manufacturer: Upofloor

Test Method Conducted
ASTM F 1914 Standard Test Method for
Short-Term Indentation and Residual Indentation of Resilient Floor Covering
Re: ASTM F1700 Standard Specification for Solid Vinyl Floor Tile

Scope:

This method covers the determination of short-term indentation and residual indentation of resilient nontextile floor coverings, such as vinyl plastic, linoleum, and felt-backed materials, when subjected to a concentrated load.

Specified Load: 140 lbs.

TEST RESULTS	
Original Thickness	0.075"
Final Thickness	0.072"
Residual Indentation	0.003"

Percentage: 4.0



President L. Kent Suddeth

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of Independent Textile Testing Service, Inc., must receive our prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of Independent Textile Testing Service, Inc., are not to be used under any circumstances in advertising to the general public.