

TECHNICAL DATA





ESTRAD ULTIMATE

PRODUCT








Estrad Ultimate	EN ISO 10581	Homogeneous sheet vinyl for public spaces
Application	EN ISO 10874	23/34/43



SPECIFICATION


































Thickness		EN ISO 24346	2.0 mm
Weight		EN ISO 23997	2800 g/m ²
Roll length		EN ISO 24341	20 m
Width		EN ISO 24341	2 m

PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, Floorscore
Fire resistance	 EN 13501-1	B _{fl} -S1
Residual indentation	 EN ISO 24343-1	≤ 0.1 mm
Slip resistance	 EN 13893 DIN 51130	DS R10
Electrical propensity	 EN 1815	≤ 2 kV (antistatic)
Wear and scratch resistance	 EN 660-2	Class T
Effect of castor chair	 EN 425/ISO 4918	Suitable
Underfloor heating		Suitable (max +27 °C)
Clean rooms	ISO 14644-1	Class 4



COLLECTION COLOURS
ESTRAD ULTIMATE

					
15201	15202	15203	15204	15205	15206
					
15220	15221	15223	15224	15225	15226
					
15227	15228	15229	15232	15249	15259
					
15251	15252	15253	15254	15255	15256
					
15258	15261	15262	15263	15264	15265
					
15267	15268	15269			