

# TECHNICAL DATA

## ZERO SOUND





### ENOMER® CONTRACT SHEET FLOORING

#### PRODUCT










Zero Sound	EN 14565	PVC- and plasticizer free Enomer® flooring with additional acoustic qualities
Application	EN ISO 10874	23/33/42



#### SPECIFICATION

Thickness	 EN ISO 24346	3.6 mm
Weight	 EN ISO 23997	3800 g/m <sup>2</sup>
Roll length	 EN ISO 24341	8 - 16 m
Width	 EN ISO 24341	145 cm


#### PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, Floorscore
Fire resistance	 EN 13501-1	C <sub>fl</sub> -s1
Residual indentation	 EN ISO 24343-1 (2.5 h)	approx. 0.13 mm
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R9
Electrical propensity	 EN 1815	≤ 2 kV (antistatic)
Chemical Resistance	 EN ISO 26987	Excellent
Underfloor heating		Suitable (max. +28 °C)
Insulation resistance	 EN 1081	> 100 GΩ
Thermal resistance	 EN 12667	R = 0.030 [m <sup>2</sup> K/W]
Impact sound reduction	 ISO 717-2	ΔL <sub>w</sub> ~ 16 dB
Resistance to bacteria and fungi	ISO 846	Good




5802 CAPE COD

NCS S 2500-N




5803 PEWTER

NCS S 4500-N



5805 GRAPHITE

NCS S 7500-N



5811 SILVER GREY

NCS S 3000-N



5822 DUSTY

NCS S 2005-Y30R



5823 MOROCCO

NCS S 4010-Y30R




5824 CORUNDUM

NCS S 6005-Y50R




5829 SUNBEAM

NCS S 2030-Y20R




5832 CAROTENE

NCS S 2060-Y40R




5843 TERRACOTTA

NCS S 2060-Y80R




5852 BLUE MOON

NCS S 5020-R80B




5858 BLUE ORCHID

NCS S 4020-R90B




5859 DENIM

NCS S 6020-B




5862 THORN APPLE

NCS S 2030-G60Y



5863 SPRUCE

NCS S 3040-G30Y



5864 AMBROSIA

NCS S 2005-G30Y