

TECHNICAL DATA

ZERO TILE




ENOMER® CONTRACT TILE FLOORING

PRODUCT












Zero Tile	EN 14565	PVC- and plasticizer-free Enomer® flooring tile
Application	EN ISO 10874	23/34/43



SPECIFICATION

Thickness	 EN ISO 24346	2.0 mm
Weight	 EN ISO 23997	3400 g/m ²
Tile size	 EN ISO 24342	500 x 500 mm
Packaging unit		5 m ² (20 tiles)

PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, Floorscore, Austrian Ecolabel
Fire resistance	 EN 13501-1	B _f -s1
Residual indentation	 EN ISO 24343-1 (2.5 h)	< 0.05 mm
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R9
Electrical propensity	 EN 1815	≤ 2 kV (antistatic)
Wear and scratch resistance	 EN 660-2 ISO 5470-1	≤ 2.0 mm ³ (Class T) 0.05 g/1000 cycles
Effect of castor chair	 EN 425	Suitable
Dimensional stability	 EN ISO 23999 (50 °C/6 h)	< 0.2%
Colour fastness	 EN ISO 105-B02	≥ 6
Flexibility	 EN ISO 24344 Method A	< 40 mm
Chemical Resistance	 EN ISO 26987	Excellent
Underfloor heating		Suitable (max. +28 °C)
Resistance to bacteria and fungi	EN 846	Good


Kährs

COLLECTION
ZERO TILE
ENOMER® CONTRACT TILE FLOORING




5102 CAPE COD

NCS S 2500-N




5103 PEWTER

NCS S 4500-N




5104 STONE GREY

NCS S 6000-N




5105 GRAPHITE

NCS S 7500-N



5111 SILVER GREY

NCS S 3000-N



5112 CONCRETE

NCS S 3502-Y



5122 DUSTY

NCS S 2005-Y30R